

EXHIBIT A



DLA Approved Independent Testing Laboratory

4207-1 Milgen Road, Columbus, GA 31907

Telephone: 844-309-6337

www.texttest.com

TexTesT Report: 12438
 Date: 8/10/2021
 Page: 1 of 1

CLIENT: **SHEEHAN & ASSOCIATES, P.C.**
 60 Cuttermill Road
 Great Neck, NY 11021

ATTN: Spencer Sheehan

SAMPLE IDENTIFICATION: 65% PIMA COTTON/35% OTHER COTTON
 SAMPLE #1 PERRY ELLIS Size: M
 Made in Vietnam STYLE: 4FMK7141RT COLOR: 308-DARK OLIVE
 Barcode 030672843087 PO: RT23236

SAMPLE #1
FIBER LENGTH AND DISTRIBUTION
ASTM D 5103

Length Group	Number of	Percent of
Lower Limit	Fibers	Total
(in.)		
2.040	0	0
1.920	0	0
1.800	0	0
1.680	0	0
Extra Long 1.560	0	0
Long 1.440	0	0
Medium 1.320	0	0
Short 1.200	0	0
1.080	0	0
0.960	0	0
0.840	10	10
0.720	47	47
0.600	41	41
0.480	2	2
0.360	0	0
0.240	0	0
0.120	0	0
0.000	0	0
	100	100

Probability 0%
 PIMA Cotton

Total
 Average Length 0.743 "
 Standard Deviation 0.08 %
 Coefficient of Variation 0.105 %
 Maximum 0.959 "
 Minimum 0.575 "


TEXTTEST

Sample Returned to Client

Ann R. Underwood
 signed by

TexTest Report: 12438
 Date: 8/10/2021
 Page: 2

SAMPLE IDENTIFICATION: 65% PIMA COTTON/35% OTHER COTTON
 SAMPLE #1 PERRY ELLIS Size: M
 Made in Vietnam STYLE: 4FMK7141RT COLOR: 308-DARK OLIVE
 Barcode 030672843087 PO: RT23236



SUMMARY COMPARISON 1

Average Length inches 0.743
 Std. Deviation 0.078
 Coefficient of Variation 0.105 %

American Pima Standard 1.2 to 1.48"
 Supima Standard 1.25" to 1.56"
 Egyptian ELS Std 1.5" to 2.5"
 GIZA 87 93 Std. 1.4 to 1.45"
 Short Fiber Content= Less the 0.5"